


## Test report

Job no. : C2300539-2  
 Tester : BT  
 Notes : SAMPLE ID-100MM SAMPLE WITH HIGHER WEFT DENIER  
 Pre-load : 1 N  
 Test speed : 300 mm/min

### Test results:

No.	F <sub>max</sub> N/mm	F (0.5 %) N/mm	F (1 %) N/mm	F (1.5 %) N/mm	F (2 %) N/mm	dL at F <sub>max</sub> %
1	150.27	0.75	1.96	3.84	6.41	20.38
2	147.42	0.81	2.08	4.04	6.73	17.30
3	165.75	0.83	2.13	4.15	6.89	19.93
4	160.61	1.18	2.76	5.12	8.34	18.70
5	166.02	0.98	2.42	4.60	7.54	19.50

### Series graph:



### Statistics:

Series n = 5	F <sub>max</sub> N/mm	F (0.5 %) N/mm	F (1 %) N/mm	F (1.5 %) N/mm	F (2 %) N/mm	dL at F <sub>max</sub> %
$\bar{x}$	158.01	0.91	2.27	4.35	7.18	19.16
s	8.70	0.17	0.32	0.51	0.77	1.21
v [%]	5.51	19.19	14.08	11.79	10.71	6.32