


Test report

Job no. : C2300539-1
 Tester : BT
 Notes : SAMPLE ID-90MM SAMPLE WITH LESSER WEFT DENIER
 Pre-load : 1 N
 Test speed : 300 mm/min

Test results:

No.	F _{max} N/mm	F (0.5 %) N/mm	F (1 %) N/mm	F (1.5 %) N/mm	F (2 %) N/mm	dL at F _{max} %
1	167.97	0.97	2.51	4.83	8.00	19.23
2	169.33	0.88	2.33	4.54	7.57	19.53
3	167.15	1.26	3.00	5.55	8.94	19.73
4	179.43	1.21	3.17	6.10	10.06	19.83
5	166.30	1.21	3.08	5.78	9.37	19.18

Series graph:



Statistics:

Series n = 5	F _{max} N/mm	F (0.5 %) N/mm	F (1 %) N/mm	F (1.5 %) N/mm	F (2 %) N/mm	dL at F _{max} %
\bar{x}	170.04	1.11	2.82	5.36	8.79	19.50
s	5.37	0.17	0.37	0.66	1.01	0.29
v [%]	3.16	15.44	13.23	12.23	11.52	1.49