



Aura Color Chem Industry


*Colors For Inspiration*TM



REACTIVE DYES
for dyeing cellulosic fibres

"VINYL SULPHONE" SERIES

For Warm Exhaust and Pad Dyeing with excellent wet fastness

 "VS" DYES	100% Cotton at 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY		
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105-C06)	RUBBING FASTNESS X=12		EXHAUST DYEING	COLD PAD BATCH	STEAM PRINTING (10-15min 103°C)
								WET	DRY			
Yellow FG (Yellow 42)		3%	M	100	G	4-5	4-5	4-5	4-5	+	+	+
Yellow GR (Yellow 15)		3%	M	100	G	4-5	4-5	4-5	4-5	+	+	+
Yellow GL (Yellow 37)		3%	M	100	G	4-5	4-5	4-5	4-5	+	+	+
Gol. Yellow RNL (Orange 107)		3%	M	100	G	3-4	4	3-4	4	+	+	+
Orange 3R (Orange 16)		3%	M	75	G	4-5	4	4	4	+	+	+
Orange W-3R (Orange 78)		3%	H	100	G	3-4	4	4	4	+	+	+
Red RB (Red 198)		3%	M	100	F	4-5	4-5	4	4	+	+	+
Red W-B (Red 264)		3%	M	110	G	3-4	4-5	3-4	4	+	+	+
Blue BB 133% (Blue 220)		3%	M	80	G	3-4	4-5	4	5	+	+	+
Blue R Sp. 150% (Blue 19)		3%	M	80	P	4-5	4-5	5	4-5	+	+	+
Turq. Blue G 266% (Blue 21)		3%	M	65	P	3-4	3-4	3-4	4	+	+	+
Black B 133% (Black 5)		3%	M	130	G	4	4-5	3-4	4-5	+	+	+

"ME" SERIES

For Warm Exhaust with good fastness and good reproducibility

 "ME DYES"	100% COTTON AT 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY		
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		EXHAUST DYEING	CONTINUOUS DYEING	COLD PAD BATCH
								WET	DRY			
Yellow ME4GL (Yellow 160A)		3%	M	110	G	4-5	4-5	4	4-5	+	+	+
Yellow MERL (Yellow 145)		3%	M	100	G	4-5	4-5	4	4-5	+	+	+
Orange ME2RL (Orange 122)		3%	M	60	F	3-4	4	3-4	4	+	+	+
Red ME4BL (Red 195)		3%	M	100	F	4	4-5	4	4-5	+	+	+
Red ME6BL (Red 250)		3%	M	70	F	3-4	4	4	5	+	+	-
Red BS (Red 111)		3%	M	110	P	3-4	4	3-4	4	+	+	-
Red RBN (Red 198A)		3%	M	100	P	3-4	4	3-4	4	+	+	-
Red ME3BL (Red 194)		3%	M	100	P	3-4	4	4	3-4	+	+	-
Red ME3GL (Red 223)		3%	H	100	G	4-5	4-5	4	4	+	+	+
Blue BRF (Blue 221)		3%	H	100	F	5	4	4-5	4	+	+	+
Ocean Blue SR		3%	H	100	P	4-5	4	4-5	4	+	+	+
Blue BRN (Blue 222)		3%	H	100	G	4-5	4	3-4	4	+	+	+
Navy Blue ME2RL (Blue 248)		3%	H	100	P	4	3-4	3-4	4	+	+	-


"SUPERIOR BLACK" SERIES

For Warm Exhaust and Pad Dyeing with excellent wet fastness

 "BLACK" DYES	100% COTTON AT 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY	
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		EXHAUST DYEING	COLD PAD BATCH
								WET	DRY		
Black DN Conc.		6%	H	100	G	4	4-5	4	4-5	+	+
Ultra Black NN		6%	H	100	G	4	4-5	4	4-5	+	+
Black WNN		6%	H	100	G	4	4-5	4	4-5	+	+
ULTRA Black XR		6%	H	100	G	4	4-5	4	4-5	+	+
ULTRA Black XG		6%	H	100	G	4	4-5	4	4-5	+	+


"RR" SERIES

For Warm Exhaust dyeing with perfect combination for medium to pale shades (High Light Fastness)

 "RR" DYES	100% COTTON AT 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY	
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS AT 3% SHADE		EXHAUST DYEING	
								WET	DRY		
Yellow RR		3%	M	110	F	4-5	4-5	4	4-5	+	
Orange RR		3%	M	100	P	4-5	3-4	4	4	+	
Red RR		3%	M	100	F	4-5	4-5	4	5	+	
Blue RR		3%	M	100	G	4-5	4	3-4	4-5	+	

"RGB" SERIES

For warm exhaust and pad dyeing. economical for medium to dark shades Suitable for trichromy shades.

 "RGB DYES"	100% COTTON AT 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY	
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS 3% Shade		EXHAUST DYEING	COLD PAD BATCH
								WET	DRY		
Gol. Yellow RGB		3%	M	110	G	4	4-5	4	4-5	+	+
Red RGB		3%	M	100	F	4-5	4-5	4	5	+	+
Blue RGB		3%	M	100	G	3-4	4	3-4	4-5	+	+
Navy Blue RGB		3%	M	100	G	3-4	4-5	3-4	4-5	+	+
Deep Black RGB		6%	M	100	G	3-4	4	3	4	+	+




"ULTRA RGB" SERIES

For warm exhaust and pad dyeing, economical for medium to dark shades

Ultra Yellow RGB		3%	M	100	F	3	4-5	4-5	4	+	+
Ultra Orange RGB		3%	M	100	G	3	4-5	3-4	4-5	+	+
Ultra Red RGB		3%	M	100	F	4	4	4	4	+	-
Ultra Carmine RGB		3%	M	100	G	4	4	3-4	4-5	+	+
Ultra Navy RGB		3%	M	100	G	3-4	4	3	4	+	+

"ED" SERIES

For Medium to Dark Shades

 "ED" DYES	100% Cotton at 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		EXHAUST DYEING
								WET	DRY	
Yellow ED		3%	H	100	F	4-5	4-5	4	4-5	+
Orange ED		3%	H	100	G	4	3-4	4	4	+
Deep Orange 4R		3%	H	100	G	4	4-5	4	4	+
Deep Cherry SD		3%	H	100	F	4-5	4	4-5	4	+
Red ED4B		3%	H	100	F	3-4	4	3-4	4	+
Red ED7B		3%	H	100	F	4	4-5	4	4-5	+
Deep Night SR		3%	H	100	G	4-5	4	4-5	4	+
Navy ED		3%	H	100	G	4-5	4	4	3-4	+
Blue LED		3%	M	110	F	4-5	4	4-5	4	+
Blue EDG		3%	M	100	G	4-5	4	4-5	4	+

"MONOCHLORO TRIAZYNL" SERIES FOR PRINTING

 "P" DYES	100% Cotton at 60°C	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				STEAM PRINTING (10-15 MIN 103°C)
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		
								WET	DRY	
Yellow P-4G (Yellow 18)		3%	M	70	G	4-5	4-5	4-5	4-5	+
Yellow P-6G (Yellow 95)		3%	H	70	G	4	4-5	4	4-5	+
Gol. Yellow P-2R (Orange 12)		3%	H	100	G	4	4-5	3-4	4-5	+
Orange P-2R (Orange 13)		3%	M	60	F	3-4	4	3-4	4	+
Red PB (Red 24)		3%	M	100	P	4-5	4	4	4	+
Red P4B (Red 245)		3%	H	100	P	3-4	4	4	4	+
Red P6B (Red 218)		3%	H	100	P	4-5	4-5	4	4	+
Turq. Blue PGR (Blue 72)		3%	M	80	P	3-4	3-4	3-4	4	+
Blue P3R (Blue 49)		3%	H	100	P	4-5	4-5	4	5	+
Navy P2R (Black 39)		6%	H	80	F	4-5	4-5	5	4-5	+
Black PGR		6%	H	100	F	3-4	3-4	3-4	4	+
Black HN (Black 8)		6%	H	50	P	4	4-5	3-4	4-5	+



Aura Color Chem Industry

Colors For Inspiration™

(STAR EXPORT HOUSE RECOGNIZED BY GOVERNMENT OF INDIA)
(FASTEST GROWING COMPANY EXCELLENCE AWARD 2023)
(An ISO 9001:2015 & 14001:2015 Certified Company)

Office Address :

© 923, Shilp Epitome, B/S Infostretch, B/H Rajpath Club Road, Bodakdev,
S.G. Highway, Ahmedabad - 380054, Gujarat, India
📞 Mobile: +91-9909006682 ✉ E-mail : sales@auraindustry.com
🌐 Website: www.auraindustry.com

Works Address :

© Plot No. C-1, Phase-2, G.I.D.C., Vatva, Ahmedabad - 382 445
Gujarat, India